



## PRODUCT PROFILE

### GENERIC DESCRIPTION

Ultra-High Build, Structural-Grade Applied Microfiber Reinforced Polymer (FRP) Polycyclic Epoxy

### COMMON USAGE

Epoxytec CPP Sprayliner™ is a two-component, 100% solids, ultra-high build, spray-applied high strength and reinforced polycyclic amine epoxy system. Formulated specifically for rehabilitation and lining of wastewater treatment plant (WWTP) structures, and other large wall, open or semi-open structures; designed with high moisture tolerance with H<sub>2</sub>S resistance and sealed I&I barrier protection. Designed for spray applicators seeking to utilize plural component heated spray application. The material can be sprayed ultra-high build, up to 3/8" (375 mils). Blended with reinforcing agents and various microfibers, Epoxytec CPP Sprayliner™ creates an applied reinforced liner as a microfiber-reinforced polymer (FRP), with high mechanical strength to protect against corrosion and seal I&I.

### COLORS

5032 Structural Gray

### FINISH

Orange-peel

## COATING SYSTEM

### SURFACER/FILLER/PATCHER

Mortartec Ceramico, Mortartec Silicate, Series 217.

### PRIMERS

Self-priming, SE-d Primecoat

## SURFACE PREPARATION

### CONCRETE

Allow new cast-in-place concrete to cure a minimum of 28 days at 75°F (24°C). Prepare the concrete by abrasive blasting, high or ultra-high pressure water cleaning, and/or approved mechanical methods to achieve clean, sound, and profiled concrete in accordance with SSPC-SP13/NACE No. 6 "Surface Preparation of Concrete." A minimum ICRI

profile of CSP 5 or higher shall be achieved with a minimum pH 9. Large cracks, voids and other surface imperfections should be filled with a recommended filler or surfacer. **Note:** Epoxytec CPP Sprayliner™ is self-priming and may be applied direct to concrete (DTC). However, should an abnormal or conditional situation exist (i.e. outgassing, MVT, etc), primers and/or resurfacers (although optional) can assist, and may be recommended.

### STEEL

Before preparing steel, please inspect and remove oil, grease, or other contaminants. Abrasive blasting (or other approved mechanical methods) must be used in order to achieve a clean surface in accordance with SSPC-SP10/NACE No. 2 "Near White Blast Cleaning" and a minimum profile of 4.0 mils (100 microns). To prevent flash rusting, consider the use of a Tnemec recommended holding primer.

### ALL SURFACES

Surface must be clean, sound, and profiled. Remove all dust, contaminants, grease, curing compounds, rust, impregnation, waxes, foreign particles, and disintegrated materials from the surface, in order to achieve a clean and profiled surface. Methods outlined herein are a basis of design for generalized guidance. Refer to epoxytec.com for additional system design detail and guidelines; please consult with your Tnemec representative on other specific design considerations.

## TECHNICAL DATA

### VOLUME SOLIDS

100%

### RECOMMENDED DFT

**Mild Conditions as a Protective Coating, Non-Structural:**

80.0 mils (2030 microns) minimum.

**I&I or Aggressive Conditions, as a High Strength Liner,**

**Structural Film:** 125.0 mils (3175 microns) minimum.

**Note:** "Structural" reference herein describes an applied and bonded high-strength film designed to hold back low pressure inflow/infiltration (I&I) and other low pressure water transmission through concrete. For structures requiring fully structural design consideration, criteria and variables will need to be calculated for specific design thickness recommendations by a licensed professional engineer.



**TECHNICAL DATA (cont.)**

**CURING TIME**

Temperature	Full Cure
140°F (60°C)	30-45 minutes
120°F (49°C)	2-4 hours
95°F (35°C)	10-12 hours
77°F (25°C)	18-24 hours

**VOLATILE ORGANIC COMPOUNDS (VOCs)**

0.04 lbs/gal (5 g/l)

**THEORETICAL COVERAGE**

1,604 mil sq ft/gal (39.3 m<sup>2</sup>/L at 25 microns). See APPLICATION for coverage rates.

**NUMBER OF COMPONENTS**

Two: Part A (Epoxy) and Part B (Amine).

**MIXING RATIO**

By volume: one (Part A) to one (Part B).

**PACKAGING**

	Part A (partially filled)	Part B (partially filled)	Yield (mixed)
Extra Large Kit	55 gallon drum	55 gallon drum	100 gallons (378.6 L)
Large Kit	6 gallon pail	6 gallon pail	10 gallons (37.9 L)

**NET WEIGHT PER GALLON**

9.82 ± 0.25 lbs (4.5 ± 0.11 kg) (mixed)

**STORAGE TEMPERATURE**

For optimum handling and application characteristics both material components should be stored or conditioned between 70°F (21°C) and 85°F (29°C) 48 hours prior to use.

**TEMPERATURE RESISTANCE**

Contact your Tnemec representative for more information.

**SHELF LIFE**

12 months at recommended storage temperatures.

**FLASH POINT - SETA**

>230°F (110°C)

**HEALTH AND SAFETY**

This product contains chemical ingredients which are considered hazardous. Read container label warning and Safety Data Sheet for important health and safety information prior to the use of this product. **Keep out of the reach of children.**

**APPLICATION**

**COVERAGE RATES**

	Dry Mills (Microns)	Wet Mills (Microns)	Sq Ft/Gal (m <sup>2</sup> /Gal)
Minimum (Non-Structural)	80.0 (2030)	80.0 (2030)	20.0 (1.86)
Minimum (Structural Film)	125.0 (3175)	125.0 (3175)	12.8 (1.19)
Maximum (per coat)	375.0 (9525)	375.0 (9525)	4.28 (0.4)

**MIXING**

Requires specialized plural application equipments. See APPLICATION EQUIPMENT.

**THINNING**

Do not thin.

**PURGE TIME**

3 minutes at 105°F (42°C)

**APPLICATION EQUIPMENT**

Epoxytec CPP Sprayliner™ is designed to be sprayed utilizing specialized equipment sold by approved equipment vendors of Epoxytec. This is a heated, plural component system. Epoxytec limits the sale of Epoxytec CPP Sprayliner™ for warranty until all equipment and know-how is validated. For detailed spray equipment specifications, heating, pressure, power, hose specs, purging/cleaning requirements or designs-contact Tnemec Technical Services.

**SURFACE TEMPERATURE**

Minimum 45°F (7°C) Maximum 130°F (54°C)

**APPLICATION (cont.)**

**MATERIAL TEMPERATURE**

Epoxytec CPP Sprayliner™ is designed to be sprayed utilizing specialized heated plural component. Material conditioning parameters are detailed on spray equipment specifications and Application Guide - contact Tnemec Technical Services.

**CLEANUP**

Purge and clean with Epoxytec Cut 5 solvent or Tnemec No. 42 Thinner.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Epoxytec LLC warrants only that its coatings represented herein meet the formulation standards of Epoxytec LLC. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Epoxytec LLC shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Epoxytec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Epoxytec makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.