

SERIES 457 | CPP SPRAYLINER 61™



PRODUCT PROFILE

GENERIC DESCRIPTION

Ultra-High Build, Structural-Grade Applied Microfiber Reinforced Polymer (FRP) Epoxy for Potable Water

COMMON USAGE

Epoxytec CPP Sprayliner 61™ is a two-component, 100% solids, ultra-high build, spray-applied, high strength and reinforced polycyclic amine epoxy system. Formulated specifically for use in potable, drinking water environments (certified **NSF/ANSI/CAN Standard 61**). Designed for applicators seeking to spray with plural-component equipment. The material can be sprayed ultra-high build, up to 3/8" (375 mils) per pass without sag. Blended with reinforcing agents and microfibers, the Epoxytec CPP Sprayliner 61™ creates an applied microfiber-reinforced polymer (FRP), with high mechanical strength to protect against corrosion and seal I&I.

COLORS

5034 Potable Blue

FINISH

Orange-peel

SPECIAL QUALIFICATIONS

Underwriters Laboratories Inc.® classified to **NSF/ANSI/CAN Standard 61**, and the extraction requirements of **NSF/ANSI/CAN 600** for use in potable water storage.

COATING SYSTEM

SURFACER/FILLER/PATCHER

Mortartec Ceramico, Mortartec Silicate, Series 217.

PRIMERS

Self-priming

SURFACE PREPARATION

CONCRETE

Allow new cast-in-place concrete to cure a minimum of 28 days at 75°F (24°C). Prepare the concrete by abrasive blasting, high or ultra-high pressure water cleaning, and/or approved mechanical method to achieve clean, sound, and profiled concrete in accordance with SSPC-SP 13/NACE No. 6. "Surface Preparation of Concrete." A minimum ICRI profile of CSP 5 or higher shall be achieved with a minimum pH 9. Large cracks, voids and other surface imperfections should be filled with a recommended filler or surfacer. **Note:** Epoxytec CPP Sprayliner 61™ is self-priming and may be applied direct to concrete (DTC). However, should an abnormal or conditional situation exist (i.e. outgassing, MVT, etc), primers and/or resurfacers (although optional) can assist, and may be recommended.

STEEL

Before preparing steel, please inspect and remove oil, grease, or other contaminants. Abrasive blasting (or other approved mechanical methods) must be used in order to achieve a clean surface in accordance with SSPC-SP 10/NACE No. 2 "Near White Blast Cleaning" and a minimum profile of 4.0 mils (100 microns). To prevent flash rusting, consider the use of a Tnemec recommended holding primer.

ALL SURFACES

Surface must be clean, sound and profiled. Remove all dust, contaminants, grease, curing compounds, rust, impregnation, waxes, foreign particles, and disintegrated materials from the surface, in order to achieve a clean and profiled surface. Methods outlined herein are a basis of design for generalized guidance. Refer to epoxytec.com for various detailed CSI-formatted project design guidelines, and/or consult with Epoxytec for other specific design considerations.

TECHNICAL DATA

VOLUME SOLIDS

100%



TECHNICAL DATA (cont.)

RECOMMENDED DFT

Mild Conditions, as a Protective Coating, Non-Structural:

80.0 mils (2032 microns) minimum.

I&I or Aggressive Conditions, as a High Strength Liner,

Structural Film: 125.0 mils (3175 microns) minimum

For Potable Water: Refer to **Underwriters Laboratories Inc.®** website for film thickness listings.

Note: “Structural” reference herein describes an applied and bonded high-strength film designed to hold back low pressure inflow/infiltration (I&I) and other low pressure water transmission through concrete. For structures requiring fully structural design consideration, criteria and variables will need to be calculated for specific design thickness recommendations by a licensed professional engineer.

CURING TIME

Temperature	Non-Potable Water	Potable Water
140°F (60°C)	30-45 minutes	3 hours
120°F (49°C)	2-4 hours	12 hours
95°F (35°C)	10-12 hours	36 hours
77°F (25°C)	24 hours	72 hours

VOLATILE ORGANIC COMPOUNDS (VOCs)

0.04 lbs/gal (5 g/l)

THEORETICAL COVERAGE

1,604 mil sq ft/gal (39.3 m²/L at 25 microns). See APPLICATION for coverage rates.

NUMBER OF COMPONENTS

Part A (Epoxy) and Part B (Amine).

MIXING RATIO

By volume: one (Part A) to one (Part B).

PACKAGING

	Part A (partially filled)	Part B (partially filled)	Yield (mixed)
Extra Large Kit	55 gallons	55 gallons	100 gallons (378.6 L)
Large Kit	6 gallon pail	6 gallon pail	10 gallons (37.9 L)

NET WEIGHT PER GALLON

9.82 ± 0.25 lbs (4.5 ± 0.11 kg) (mixed)

STORAGE TEMPERATURE

For optimum handling and application characteristics both material components should be stored or conditioned between 70°F (21°C) and 85°F (29°C) 48 hours prior to use.

TEMPERATURE RESISTANCE

Contact your Tnemec representative for more information.

SHELF LIFE

24 months at recommended storage temperature.

FLASH POINT - SETA

>230°F (110°C)

HEALTH AND SAFETY

This product contains chemical ingredients which are considered hazardous. Read container label warning and Safety Data Sheet for important health and safety information prior to the use of this product. **Keep out of the reach of children.**

APPLICATION

COVERAGE RATES

	Dry MILS (Microns)	Wet MILS (Microns)	Sq Ft/Gal (m ² /Gal)
Minimum (Non-Structural)	80.0 (2032)	80.0 (2032)	20 (1.86)
Minimum (Structural Film)	125.0 (3175)	125.0 (3175)	12.8 (1.19)
Maximum (per coat)	375.0 (9525)	375.0 (9525)	4.28 (0.4)

Note: For potable water applications, visit **Underwriters Laboratories Inc.®** website for current film thickness listings.

APPLICATION (cont.)

MIXING

Requires specialized plural application equipments. See APPLICATION EQUIPMENT

THINNING

Do not thin.

PURGE TIME

3 minutes at 105°F (41°C)

APPLICATION EQUIPMENT

Epoxytec CPP Sprayliner 61™ is designed to be sprayed utilizing specialized equipment sold by approved equipment vendors of Epoxytec. This is a heated, plural component system. Epoxytec limits the sale of Epoxytec CPP Sprayliner 61™ for warranty until all equipment and know-how is validated. For detailed spray equipment specifications, heating, pressure, power, hose specs, purging/cleaning requirements or designs- contact Tnemec Technical Services.

SURFACE TEMPERATURE

Minimum 45°F (7°C) Maximum 130°F (54°C)

MATERIAL TEMPERATURE

Epoxytec CPP Sprayliner 61™ is designed to be sprayed utilizing specialized heated plural component. Material conditioning parameters are detailed on spray equipment specifications and Application Guide - contact Tnemec Technical Services.

CLEANUP

Purge and clean with Epoxytec Cut 5 solvent or Tnemec No. 42 Thinner.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Epoxytec LLC warrants only that its coatings represented herein meet the formulation standards of Epoxytec LLC. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Epoxytec LLC shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Epoxytec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Epoxytec makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.